

Please amend the Application as follows.

**IN THE CLAIMS:**

Please replace Claims 1, 5, 13 and 15 with the following.

---

1. (Twice Amended, Clean) A thermoplastic moulding composition comprising:

A) 40 to 99 parts by weight of at least one of aromatic polycarbonate and polyester carbonate;

B) 0.5 to 60 parts by weight of a graft polymer prepared from,



B.1) 5 to 95 wt.% of one or more vinyl monomers, and

B.2) 95 to 5 wt.% of one or more particulate diene rubbers having a glass transition temperature of  $<10^{\circ}\text{C}$ , which are produced by emulsion polymerisation,

said graft polymer being prepared by means of a graft polymerisation in the presence of an initiator system comprising an organic hydroperoxide and ascorbic acid, said graft polymerisation having a grafting yield of  $> 60$  wt.%;

C) 0 to 45 parts by weight of at least one thermoplastic polymer selected from the group consisting of thermoplastic vinyl (co)polymers and polyalkylene terephthalates;

D) 0.1 to 50 parts by weight of at least one component selected from the group consisting of phosphazenes represented by the following formulae,



in which

R is in each case identical or different and denotes amino, C<sub>1</sub> to C<sub>8</sub> alkyl, in each case optionally halogenated, or C<sub>1</sub> to C<sub>8</sub> alkoxy, C<sub>5</sub> to C<sub>6</sub> cycloalkyl, C<sub>6</sub> to C<sub>20</sub> aryl, C<sub>6</sub> to C<sub>20</sub> aryloxy, or C<sub>7</sub> to C<sub>12</sub> aralkyl, in each case optionally substituted by alkyl and/or halogen,

k denotes 0 or a number from 1 to 15; and

E) 0 to 5 parts by weight of fluorinated polyolefin.

5. (Thrice Amended, Clean) The moulding composition of Claim 1 wherein vinyl monomers B.1 are mixtures prepared from:

B.1.1 50 to 99 parts by weight of at least one member selected from the group consisting of vinyl aromatics, ring-substituted vinyl aromatics and methacrylic acid (C<sub>1</sub>-C<sub>8</sub>)-alkyl esters; and

B.1.2 1 to 50 parts by weight of at least one member selected from the group consisting of vinyl cyanides, (meth)acrylic acid (C<sub>1</sub>-C<sub>8</sub>)-alkyl esters, anhydrides of unsaturated carboxylic acids and imides of unsaturated carboxylic acids.

C3 13. (Thrice Amended, Clean) The moulding composition of Claim 1 further comprising at least one additive selected from the group consisting of lubricants, mould release agents, nucleating agents, anti-static agents, stabilisers, dyes and pigments.

C4 15. (Twice Amended, Clean) A method of producing the moulding composition of Claim 1 comprising mixing and melt-compounding components A to E and optionally at least one additive selected from the group consisting of lubricants, mould release agents, nucleating agents, anti-static agents, stabilisers, dyes and pigments.